


(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau(43) International Publication Date
1 April 2004 (01.04.2004)

PCT

(10) International Publication Number
WO 2004/027133 A1

- (51) International Patent Classification⁷: **D02J 1/22** [JP/JP]; 798-113, Ryuji, Futaba-cho, Kitakoma-gun,, Yamanashi, 407-0104 (JP).
- (21) International Application Number: **PCT/JP2003/002727**
- (22) International Filing Date: **7 March 2003 (07.03.2003)**
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:
2002-307633 17 September 2002 (17.09.2002) JP
- (71) Applicant (for all designated States except US): **YAMANASHI TLO CO., Ltd [JP/JP]; 3-11, Takeda 4-chome, Kofu-shi,, Yamanashi, 400-8511 (JP).**
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): **SUZUKI, Akihiko**
- (74) Agent: **KURIHARA, Kazuhiko; KURIHARA PATENT OFFICE, 11-5-1002, Takashimadaira 3-chome, Itabashi-ku, Tokyo 175-0082 (JP).**
- (81) Designated States (national): **CN, KR, US.**
- (84) Designated States (regional): **European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).**
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: HIGHLY ORIENTED SUPER MICROFILAMENTS

(57) **Abstract:** Method of and apparatus for continuously manufacturing highly oriented super micro filaments with a diameter of 5 μ m or less from most of thermoplastic polymers stably by a simple and convenient means without requiring any special apparatus of high accuracy and high level, characterized in original filaments supplied from a filament supply means are heated by infrared beams and the heated filaments are drawn by tension provided by their own weight or under an applied tension of 1 MPa or less, and are drawn to 1000 times or more.